

Lenzing Jacketing 524



Lenzing Plastics GmbH
 A-4860 Lenzing, Austria
 Tel.: +43 7672 701-3712
 Fax: +43 7672 918-3712
 E-mail: jacketing@lenzing.com
www.lenzing.com

Lenzing JACKETING 524 is a double layer laminate of aluminum, coated with a special UV protection and a PVC backing. This system is highly puncture and tear resistant as well as flame retardant and can be used for exterior and interior facing of hot and cold insulation. It combines an excellent vapour barrier with water tightness. Due to the curling effect, Lenzing Jacketing 524 is particularly suitable for insulation application especially on pipes, even for small diameters.

Construction:



- UV-protection
- Aluminium, glossy
- PVC, fire-retardant

Technical data:

Total weight:	approx.	512 g/m ²	EN 22 286
Thickness:	approx.	350 µm	
Tensile strength:	MD	290 N/15 mm	EN ISO 527-3
	CD	250 N/15 mm	EN ISO 527-3
Elongation:	MD	35 %	EN ISO 527-3
	CD	30 %	EN ISO 527-3
Tear strength:	MD	90 N	EN ISO 527-3
	CD	70 N	EN ISO 527-3
Puncture Ø 0,8mm:		28 N	prEN 14 477
Puncture Ø 3,0mm: (from alu-side)		116 N	prEN 14 477
Nail tear strength:	MD	63 N	EN 12310-1
	CD	83 N	EN 12310-1
Limited oxygen indication LOI:		35,5 %O ₂	ASTM D 2863-77 ISO 4589
UV-light resistance testing:			ASTM G 26A ISO 4892-2
Water vapour permeability WVTR:		< 0,03 g/m ² /d	ASTM F1249 ISO 15106-2
Sd-value:		>1.300 m	
Emission ratio:		approx. 94 %	
Temperature resistance:		-25 to +75 °C	
Fire classes:	Class 0		BS 476, part 6 & 7
	Class 1		UL 94 V
	B1		DIN 4102-1
Radiant panel index		0,37	ASTM E162-02e
Flaming mode 1,5 min.		1	ASTM E662-03
Flaming mode 4 min.		3	ASTM E662-03
Non-Flaming mode 1,5 min.		0	ASTM E662-03
Non-Flaming mode 4 min.		0	ASTM E662-03

Material testing:

according to internal material specification

Mat.No.: 77019536
 Doc.No.: PS005506 / 3
 Edition: Jul.07

Subject to change without notice. All internal measured values must be seen as benchmarks without any claim for guarantee.



Lenzing Jacketing can be installed on pipes, ducts, containers, tanks, etc.