

# Lenzing JACKETING 528



Lenzing Plastics GmbH  
A-4860 Lenzing, Austria  
Tel.: +43 7672 701-3712  
Fax: +43 7672 918-3712  
E-mail: [jacketing@lenzing.com](mailto:jacketing@lenzing.com)  
[www.lenzing.com](http://www.lenzing.com)

Lenzing JACKETING 528 is a double layer laminate of aluminum, coated with a special UV protection and a PVC backing. This system is highly puncture and tear resistant as well as flame retardant and can be used for exterior and interior facing of hot and cold insulation. It combines an excellent vapour barrier with water tightness.

## Construction:



- UV-protection
- Aluminium, glossy
- PVC, fire-retardant

## Technical data:

<b>Total weight:</b>	approx.	512 g/m <sup>2</sup>	EN 22 286
<b>Thickness:</b>	approx.	350 µm	
<b>Tensile strength:</b>	MD	290 N/15 mm	EN ISO 527-3
	CD	250 N/15 mm	EN ISO 527-3
<b>Elongation:</b>	MD	35 %	EN ISO 527-3
	CD	30 %	EN ISO 527-3
<b>Tear strength:</b>	MD	90 N	EN ISO 527-3
	CD	70 N	EN ISO 527-3
<b>Puncture Ø 0,8mm:</b>		28 N	prEN 14 477
<b>Puncture Ø 3,0mm:</b> (from alu-side)		116 N	prEN 14 477
<b>Nail tear strength:</b>	MD	63 N	EN 12310-1
	CD	83 N	EN 12310-1
<b>Limited oxygen indication LOI:</b>		35,5 %O <sub>2</sub>	ASTM D 2863-77 ISO 4589
<b>UV-light resistance testing:</b>			ASTM G 26A ISO 4892-2
<b>Water vapour permeability WVTR:</b>		< 0,03 g/m <sup>2</sup> /d	ASTM F1249 ISO 15106-2
<b>Sd-value:</b>		>1.300 m	
<b>Emission ratio:</b>		approx. 94 %	
<b>Temperature resistance:</b>		-25 to +75 °C	
<b>Fire classes:</b>		Class 0	BS 476, part 6 & 7
		Class 1	UL 94 V
		B1	DIN 4102-1
<b>Radiant panel index</b>		0,37	ASTM E162-02e
<b>Flaming mode 1,5 min.</b>		1	ASTM E662-03
<b>Flaming mode 4 min.</b>		3	ASTM E662-03
<b>Non-Flaming mode 1,5 min.</b>		0	ASTM E662-03
<b>Non-Flaming mode 4 min.</b>		0	ASTM E662-03



Lenzing JACKETING 528 can be installed on pipes, ducts, tanks, etc

## Material testing:

according to internal material specification

Mat.No.: 77019003  
Doc.No.: PS012905 / 4  
Edition: Jul.07

Subject to change without notice. All internal measured values must be seen as benchmarks without any claim for guarantee.